

Certificate Of Analysis

Certificate Number: **0047-22** Issue Number: **1** Issue Date: **11/03/2022 1:02:32 PM**
 Test Certificate for: **SUNLITE Cement**
 Sample Tested at: **Sunstate Cement Ltd., Port of Brisbane, Australia**
 Sample Identification: **Spot Despatch Sample L6P-001394 dated 30/01/2022**
 Sample Produced at: **Sunstate Cement Ltd., Port of Brisbane, Australia**

SPECIFIC PROPERTY	TEST METHOD	AS3972 REQUIREMENTS		RESULT
Compressive strength	AS2350.11, AS2350.12			
3 Day		Minimum	25 MPa	40.6 MPa
7 Day		Minimum	40 Mpa	48.7 MPa
28 Day				59.3 MPa
Setting Time	AS2350.4			
Initial		Minimum	45 mins	75 mins
Final		Maximum	360 mins	150 mins
Soundness	AS2350.5	Maximum	5 mm	0 mm
Sulphuric anhydride (SO₃)	In House	Maximum	3.5 %	2.8 %
Chloride	AS3583.13	Maximum	0.1 %	0.020 %
REPORTABLE PROPERTY	TEST METHOD			RESULT
Loss on ignition	AS2350.2			3.5 %
Fineness	AS2350.8			430 m²/kg
OTHER PROPERTIES	TEST METHOD			RESULT
Normal Consistency	AS2350.3			28.2 %

Sampling Procedure:

Samples were prepared in accordance with AS2350.1


Remarks:

- 1 These results only relate to the specimens identified on this report



NATA accredited
 Laboratory Number: 2191

 Accredited for compliance with
 ISO/IEC 17025 Testing



George Santagiuliana
 Approved Signature
 11/03/2022

This certificate replaces previous certificate number 0047-22, issue 0 dated (REASON: Test Data Updated)