

Certificate Of Analysis

Certificate Number: **0135-22** Issue Number: **1** Issue Date: **3/05/2022 1:20:06 PM**
 Test Certificate for: **aalWHITE**
 Sample Tested at: **Sunstate Cement Ltd., Port of Brisbane, Australia**
 Sample Identification: **Spot Despatch Sample B6P-000284 dated 5/04/2022**
 Sample Produced at: **Sunstate Cement Ltd., Port of Brisbane, Australia**

SPECIFIC PROPERTY	TEST METHOD	AS3972 REQUIREMENTS	RESULT
Compressive strength	AS2350.11, AS2350.12		
3 Day			23 MPa
7 Day		Minimum 20 MPa	35.1 MPa
28 Day		Minimum 35 Mpa	52 MPa
Setting Time	AS2350.4		
Initial		Minimum 45 mins	120 mins
Final		Maximum 600 mins	225 mins
Soundness	AS2350.5	Maximum 5 mm	2 mm
Sulphuric anhydride (SO₃)	In House	Maximum 3.5 %	2.1 %
Chloride	AS3583.13	Maximum 0.1 %	0.004 %
REPORTABLE PROPERTY	TEST METHOD		RESULT
Loss on ignition	AS2350.2		1.4 %
Fineness	AS2350.8		430 m ² /kg
OTHER PROPERTIES	TEST METHOD		RESULT
Normal Consistency	AS2350.3		32.2 %

Sampling Procedure:

Samples were prepared in accordance with AS2350.1

Remarks:

- 1 These results only relate to the specimens identified on this report



NATA accredited
 Laboratory Number: 2191
 Accredited for compliance with
 ISO/IEC 17025 Testing



George Santagiuliana
 Approved Signature
 03/05/2022

This certificate replaces previous certificate number 0135-22, issue 0 dated (REASON: Test Data Updated)