ADMIN: Phone: (07) 3895 9800 Fax: (07) 3895 9801 SALES: Phone: (07) 3985 9890 Fax: (07) 3895 9891

## **Certificate Of Analysis**

Test Certificate for: Slag Blend 30

Sample Tested at: Sunstate Cement Ltd., Port of Brisbane, Australia
Sample Identification: Spot Despatch Sample O6P-000822 dated 15/08/2022

Sample Produced at: Sunstate Cement Ltd., Port of Brisbane, Australia

SPECIFIC PROPERTY	TEST METHOD	AS3972 REQUIREMENTS		RESULT
Compressive strength	AS2350.11, AS2350.12			
3 Day				<b>26.1</b> MPa
7 Day		Minimum	20 MPa	<b>39.4</b> MPa
28 Day		Minimum	35 Mpa	<b>58.4</b> MPa
Setting Time	AS2350.4			
Inital		Minimum	45 mins	<b>120</b> mins
Final		Maximum	600 mins	<b>195</b> mins
Soundness	AS2350.5	Maximum	5 mm	<b>0</b> mm
Sulphuric anhydride (SO₃)	In House	Maximum	3.5 %	2.8 %
Chloride	AS3583.13	Maximum	0.1 %	0.006 %
REPORTABLE PROPERTY	TEST METHOD			RESULT
Loss on ignition	AS2350.2			2.8 %
Fineness	AS2350.8			<b>395</b> m²/kg
OTHER PROPERTIES	TEST METHOD			RESULT
Normal Consistency	AS2350.3			29.3 %

## **Sampling Procedure:**

Samples were prepared in accordance with AS2350.1

## Remarks:

- 1 These results only relate to the specimens identified on this report
- 2 The blended cement is produced with a nominal 30% GBFS content



NATA accredited Laboratory Number: 2191

Accredited for compliance with ISO/IEC 17025 Testing

George Santagiuliana
Approved Signature

19/10/2022