ADMIN: Phone: (07) 3895 9800 Fax: (07) 3895 9801 SALES: Phone: (07) 3985 9890 Fax: (07) 3895 9891

Certificate Of Analysis

Certificate Number: **0005-24** Issue Number: **1** Issue Date: **9/04/2024 10:29:11 AM**

Test Certificate for: SUNLITE Cement

Sample Tested at: Sunstate Cement Ltd., Port of Brisbane, Australia
Sample Identification: Spot Despatch Sample L6P-001491 dated 3/01/2024
Sample Produced at: Sunstate Cement Ltd., Port of Brisbane, Australia

SPECIFIC PROPERTY	TEST METHOD	AS3972 REQUIREMENTS		RESULT
Compressive strength	AS2350.11, AS2350.12			
3 Day		Minimum	25 MPa	39.6 MPa
7 Day		Minimum	40 Mpa	50 MPa
28 Day				62.1 MPa
Setting Time	AS2350.4			
Inital		Minimum	45 mins	90 mins
Final		Maximum	360 mins	135 mins
Soundness	AS2350.5	Maximum	5 mm	0 mm
Sulphuric anhydride (SO₃)	In House	Maximum	3.5 %	2.9 %
Chloride	AS3583.13	Maximum	0.1 %	0.020 %
REPORTABLE PROPERTY	TEST METHOD			RESULT
Loss on ignition	AS2350.2			5.2 %
Fineness	AS2350.8			425 m ² /kg
OTHER PROPERTIES	TEST METHOD			RESULT
Normal Consistency	AS2350.3			28.9 %

Sampling Procedure:

Samples were prepared in accordance with AS2350.1

Remarks:

1 These results only relate to the specimens identified on this report



NATA accredited Laboratory Number: 2191

Accredited for compliance with ISO/IEC 17025 Testing

George Santagiuliana
Approved Signature
09/04/2024