

# Certificate Of Analysis

Certificate Number: **0049-24** Issue Number: **1** Issue Date: **9/04/2024 10:25:23 AM**  
 Test Certificate for: **Slag Blend 30**  
 Sample Tested at: **Sunstate Cement Ltd., Port of Brisbane, Australia**  
 Sample Identification: **Spot Despatch Sample O6P-000893 dated 5/02/2024**  
 Sample Produced at: **Sunstate Cement Ltd., Port of Brisbane, Australia**


SPECIFIC PROPERTY	TEST METHOD	AS3972 REQUIREMENTS	RESULT
<b>Compressive strength</b>	AS2350.11, AS2350.12		
3 Day			25.5 MPa
7 Day		Minimum 20 MPa	38.5 MPa
28 Day		Minimum 35 Mpa	57 MPa
<b>Setting Time</b>	AS2350.4		
Initial		Minimum 45 mins	105 mins
Final		Maximum 600 mins	195 mins
<b>Soundness</b>	AS2350.5	Maximum 5 mm	2 mm
<b>Sulphuric anhydride (SO<sub>3</sub>)</b>	In House	Maximum 3.5 %	2.1 %
<b>Chloride</b>	AS3583.13	Maximum 0.1 %	0.007 %
REPORTABLE PROPERTY	TEST METHOD		RESULT
<b>Loss on ignition</b>	AS2350.2		3.1 %
<b>Fineness</b>	AS2350.8		465 m <sup>2</sup> /kg
OTHER PROPERTIES	TEST METHOD		RESULT
<b>Normal Consistency</b>	AS2350.3		32.1 %

**Sampling Procedure:**


Samples were prepared in accordance with AS2350.1

**Remarks:**

- 1 These results only relate to the specimens identified on this report
- 2 The blended cement is produced with a nominal 30% GBFS content



NATA accredited  
 Laboratory Number: 2191  
  
 Accredited for compliance with  
 ISO/IEC 17025 Testing



George Santagiuliana  
 Approved Signature  
 09/04/2024

***This certificate replaces previous certificate number 0049-24, issue 0 dated (REASON: Test Data Updated)***