ADMIN: Phone: (07) 3895 9800 Fax: (07) 3895 9801 SALES: Phone: (07) 3985 9890 Fax: (07) 3895 9891

Certificate Of Analysis

Certificate Number: **0131-24** Issue Number: **1** Issue Date: **9/04/2024 9:25:42 AM**

Test Certificate for: Slag Blend 60

Sample Tested at: Sunstate Cement Ltd., Port of Brisbane, Australia

Sample Identification: Spot Despatch Sample H6P-000806 dated 19/03/2024

Sample Produced at: Sunstate Cement Ltd., Port of Brisbane, Australia

| SPECIFIC PROPERTY | TEST METHOD | AS3972 REQUIREMENTS | | RESULT |
|---------------------------|----------------------|---------------------|----------|------------------|
| Compressive strength | AS2350.11, AS2350.12 | | | |
| 3 Day | | | | 18.6 MPa |
| 7 Day | | Minimum | 20 MPa | 29.5 MPa |
| 28 Day | | Minimum | 35 Mpa | MPa |
| Setting Time | AS2350.4 | | | |
| Inital | | Minimum | 45 mins | 135 mins |
| Final | | Maximum | 600 mins | 210 mins |
| Soundness | AS2350.5 | Maximum | 5 mm | 1 mm |
| Sulphuric anhydride (SO₃) | In House | Maximum | 3.5 % | 2.6 % |
| Chloride | AS3583.13 | Maximum | 0.1 % | 0.008 % |
| REPORTABLE PROPERTY | TEST METHOD | | | RESULT |
| Loss on ignition | AS2350.2 | | | 1.0 % |
| Fineness | AS2350.8 | | | 495 m²/kg |
| OTHER PROPERTIES | TEST METHOD | | | RESULT |
| Normal Consistency | AS2350.3 | | | 33.5 % |

Sampling Procedure:

Samples were prepared in accordance with AS2350.1

Remarks:

1 These results only relate to the specimens identified on this report



NATA accredited Laboratory Number: 2191

Accredited for compliance with ISO/IEC 17025 Testing



09/04/2024