Certificate Of Analysis

ADMIN: Phone: (07) 3895 9800 Fax: (07) 3895 9801

SALES: Phone: (07) 3985 9890 Fax: (07) 3895 9891

Test Certificate for: Milled Slag

Produced at: Sunstate Cement Ltd., Port of Brisbane, Australia

Monthly Composite for: June, 2024

Material Source: Nippon Steel

Point of Sampling: Final product air slide, Sunstate Cement Ltd., Port of Brisbane, Australia

Sample Tested at: Sunstate Cement Ltd., Port of Brisbane, Australia

Sample Identification: **T6M-000182**

SPECIFIC PROPERTY	TEST METHOD	AS3582.2 REQUIREMENTS		RESULT
Fineness	AS3583.1			96.0 %
Loss on ignition	AS3583.3			-0.1 %
Insoluble residue	AS3583.14			%
SO₃	InHouse			%
Magnesia (MgO)	AS2350.2	Maximum	15 %	6.3 %
Alumina (Ai₂O₃)	AS2350.2	Maximum	18 %	12.5 %
Total Iron (Fe₂O₃)	AS2350.2			1.4 %
Manganese (MnO)	AS2350.2			0.2 %
Total Alkali	AS2350.2			0.4 %
Avalible Alkali	AS3583.12			%
Chloride	AS3583.13	Maximum	0.1 %	0.003 %
Relative Density	AS3583.5			2.9 g/cm ³
Relative Water	AS3583.6			103.5 %
Relative Strength	AS3583.6			86.9 %

Sampling Procedure:

Samples obtained were in accordance with AS2350.1

Remarks:

- 1 These results only relate to the specimens identified on this report
- 2 Total Alkali determined at Australian Laboratory Services by ICP -AES using ME -ICP 91, Corporate Accreditation No 825, Corporate Site 818
- 3 XRF Analytical results determined at Australian Laboratory Services by XRF using ME -XRF 26, Corporate Accreditation No 825, Corporate Site 818
- 5 Available alkali determined by: Cement Australia Accreditation No 187 & 188



NATA accredited Laboratory Number: 2191

Accredited for compliance with ISO/IEC 17025 Testing

George Santagiuliana Approved Signature

21/10/2024