

Certificate Of Analysis

Certificate Number: **0018-25** Issue Number: **1** Issue Date: **24/04/2025 12:17:22 PM**
Test Certificate for: **SUNLITE Cement**
Sample Tested at: **Sunstate Cement Ltd., Port of Brisbane, Australia**
Sample Identification: **Spot Despatch Sample L6P-001546 dated 20/01/2025**
Sample Produced at: **Sunstate Cement Ltd., Port of Brisbane, Australia**

| SPECIFIC PROPERTY | TEST METHOD | AS3972 REQUIREMENTS | | RESULT |
|---|----------------------|---------------------|----------|-----------------------------|
| Compressive strength | AS2350.11, AS2350.12 | | | |
| 3 Day | | Minimum | 25 MPa | 44.6 MPa |
| 7 Day | | Minimum | 40 Mpa | 53.9 MPa |
| 28 Day | | | | 66.3 MPa |
| Setting Time | AS2350.4 | | | |
| Initial | | Minimum | 45 mins | 75 mins |
| Final | | Maximum | 360 mins | 165 mins |
| Soundness | AS2350.5 | Maximum | 5 mm | 1 mm |
| Sulphuric anhydride (SO₃) | In House | Maximum | 3.5 % | 3.1 % |
| Chloride | AS3583.13 | Maximum | 0.1 % | 0.027 % |
| REPORTABLE PROPERTY | TEST METHOD | | | RESULT |
| Loss on ignition | AS2350.2 | | | 4.5 % |
| Fineness | AS2350.8 | | | 420 m²/kg |
| OTHER PROPERTIES | TEST METHOD | | | RESULT |
| Normal Consistency | AS2350.3 | | | 28.5 % |

Sampling Procedure:

Samples were prepared in accordance with AS2350.1

Remarks:

- These results only relate to the specimens identified on this report



NATA accredited
Laboratory Number: 2191

Accredited for compliance with
ISO/IEC 17025 Testing



George Santagiuliana
Approved Signature

24/04/2025

This certificate replaces previous certificate number 0018-25, issue 0 dated (REASON: Test Data Updated)