

CERTIFICATE OF ANALYSIS

CERTIFICATE No. 2036-18

TEST CERTIFICATE FOR: Flyash Blend 25

PRODUCED AT: Sunstate Cement Ltd, Port of Brisbane

SAMPLE IDENTIFICATION: Spot Despatch Sample sample F6P-001227 sampled on 12/11/2018

SAMPLE TESTED AT: Sunstate Cement Ltd, Port of Brisbane

SPECIFIED PROPERTY	TEST METHOD	AS3972 REQUIREMENTS		RESULT
Compressive strength	AS2350.11, AS2350.12			
3 day				31.2 MPa
7 day		Minimum	20 MPa	41.3 MPa
28 day		Minimum	35 MPa	58.3 MPa
Setting time	AS2350.4			
Initial		Minimum	45 mins	90 mins
Final		Maximum	600 mins	165 mins
Soundness	AS2350.5	Maximum	5 mm	0 mm
Sulphuric anhydride (SO ₃)	In House	Maximum	3.5 %	1.7 %

REPORTABLE PROPERTY	TEST METHOD			RESULT
Loss on ignition	AS2350.2			1.9 %
Fineness	AS2350.8			445 m ² /kg
Chloride	AS3583.13			0.0023 %

OTHER PROPERTIES	TEST METHOD			RESULT
Normal Consistency	In House			31.5 %

SAMPLING PROCEDURE: Cement samples obtained according to the requirements of AS2350.1

REMARKS: The results of the above tests relate only to the sample as described above.
The blended cement is produced with a nominal 25% fly ash content.



G Santaguiliana
Approved Signatory
3-Jan-2019

Page 1 of 1

A.B.N. 58 010 421 879
POSTAL ADDRESS: PO BOX 350, WYNNUM, QLD. 4178
PHONE: (07) 3895 9800 FAX: (07) 3895 9801



NATA accredited laboratory
Laboratory Number: 2190 / 2191
Accredited for compliance with
ISO/IEC 17025
The results of the tests,
calibrations and/or measurements
included in this document are
traceable to Australian/national
standards. This document shall
not be reproduced except in full.