

CERTIFICATE OF ANALYSIS

**CERTIFICATE No.** 0822-19  
**TEST CERTIFICATE FOR:** Flyash Blend 25  
**PRODUCED AT:** Sunstate Cement Ltd, Port of Brisbane  
**SAMPLE IDENTIFICATION:** Spot Despatch Sample sample F6P-001284 sampled on 17/6/2019  
**SAMPLE TESTED AT:** Sunstate Cement Ltd, Port of Brisbane


SPECIFIED PROPERTY	TEST METHOD	AS3972 REQUIREMENTS		RESULT
Compressive strength	AS2350.11, AS2350.12			
3 day				25.9 MPa
7 day		Minimum	20 MPa	37.0 MPa
28 day		Minimum	35 MPa	53.1 MPa
Setting time	AS2350.4			
Initial		Minimum	45 mins	105 mins
Final		Maximum	600 mins	210 mins
Soundness	AS2350.5	Maximum	5 mm	0 mm
Sulphuric anhydride (SO <sub>3</sub> )	In House	Maximum	3.5 %	1.6 %

REPORTABLE PROPERTY	TEST METHOD	RESULT
Loss on ignition	AS2350.2	1.1 %
Fineness	AS2350.8	415 m <sup>2</sup> /kg
Chloride	AS3583.13	0.0032 %

OTHER PROPERTIES	TEST METHOD	RESULT
Normal Consistency	In House	32.4 %

**SAMPLING PROCEDURE:** Cement samples obtained according to the requirements of AS2350.1

**REMARKS:** The results of the above tests relate only to the sample as described above.  
The blended cement is produced with a nominal 25% fly ash content.



**G Santaguiliana**  
**Approved Signatory**  
**3-Sep-2019**

Page 1 of 1

A.B.N. 58 010 421 879  
**POSTAL ADDRESS: PO BOX 350, WYNNUM, QLD. 4178**  
**PHONE: (07) 3895 9800 FAX: (07) 3895 9801**



NATA accredited laboratory  
Laboratory Number: 2190 / 2191  
Accredited for compliance with  
ISO/IEC 17025  
The results of the tests,  
calibrations and/or measurements  
included in this document are  
traceable to Australian/national  
standards. This document shall not  
be reproduced except in full.