

CERTIFICATE OF ANALYSIS

CERTIFICATE No. 1541-19

TEST CERTIFICATE FOR: Type Milled Slag

PRODUCED AT: Sunstate Cement Ltd, Port of Brisbane

SAMPLE IDENTIFICATION: Monthly Composite for the month of December 2019

MATERIAL SOURCE: Nippon Steel Corporation

POINT OF SAMPLING: Final product air slide, Sunstate Cement Ltd, Port of Brisbane

SAMPLE TESTED AT: Sunstate Cement Ltd, Port of Brisbane

SAMPLE IDENTIFICATION: T6M-000126



NATA accredited laboratory
 Laboratory Number: 2191
 Accredited for compliance with
 ISO/IEC 17025 Testing
 The results of the tests,
 calibrations and/or measurements
 included in this document are
 traceable to Australian/national
 standards. This document shall not
 be reproduced except in full.

SPECIFIED PROPERTY	TEST METHOD	AS3582.1 REQUIREMENTS		RESULT
Fineness	AS 3583.1			93 %
Insoluble residue	AS 3583.14			0.4 %
Loss on ignition	AS 3583.3			0.1 %
SO3	Inhouse			2.4 %
Chemical Properties				
Sulfide sulfur (S)	AS 3583.7	Maximum	1.5 %	0.6 %
Magnesia (MgO)	AS 2350.2	Maximum	15 %	5.9 %
Alumina (Al ₂ O ₃)	AS 2350.2	Maximum	18 %	12.7 %
Total Iron (FeO)	AS 2350.2			0.8 %
Manganese (MnO)	AS 2350.2			0.2 %
Chloride	AS3583.13	Maximum	0.1 %	0.004 %
Total Alkali	AS2350.2			0.3 %
Available Alkali	AS3583.12			0.2 %
Relative Density	AS3583.5			2.8 g/cm ³
Relative Water	AS3583.6			100 %
Relative Strength	AS3583.6			86 %

SAMPLING PROCEDURE: Slag samples obtained according to the requirements of AS2349

REMARKS:

1. The results of the above tests relate only to the sample as described above.
2. Available alkali determined by: Cement Australia Accreditation No 187 & 188.



G Santaguiliana
Approved Signatory
27-Feb-2020

A.B.N. 58 010 421 870
 POSTAL ADDRESS: PO BOX 350, WYNNUM, QLD. 4178
 PHONE: (07) 3895 9800 FAX: (07) 3895 9801