

Certificate Of Analysis

Certificate Number: **1111-20** Issue Number: **1** Issue Date: **12/02/2021 3:00:02 PM**
 Test Certificate for: **Slag Blend 30**
 Sample Tested at: **Sunstate Cement Ltd., Port of Brisbane, Australia**
 Sample Identification: **Spot Despatch Sample O6P-000736 dated 9/11/2020**
 Sample Produced at: **Sunstate Cement Ltd., Port of Brisbane, Australia**

SPECIFIC PROPERTY	TEST METHOD	AS3972 REQUIREMENTS	RESULT
Compressive strength	AS2350.11, AS2350.12		
3 Day			30.0 MPa
7 Day		Minimum 20 MPa	42.2 MPa
28 Day		Minimum 35 Mpa	60.8 MPa
Setting Time	AS2350.4		
Initial		Minimum 45 mins	105 mins
Final		Maximum 600 mins	180 mins
Soundness	AS2350.5	Maximum 5 mm	1 mm
Sulphuric anhydride (SO₃)	In House	Maximum 3.5 %	2.3 %
Chloride	AS3583.13	Maximum 0.1 %	0.003 %
REPORTABLE PROPERTY	TEST METHOD		RESULT
Loss on ignition	AS2350.2		2.7 %
Fineness	AS2350.8		425 m²/kg
OTHER PROPERTIES	TEST METHOD		RESULT
Normal Consistency	AS2350.3		29.3 %

Sampling Procedure:

Samples were prepared in accordance with AS2350.1

Remarks:

- 1 These results only relate to the specimens identified on this report
- 2 The blended cement is produced with a nominal 30% GBFS content



NATA accredited
 Laboratory Number: 2191

Accredited for compliance with
 ISO/IEC 17025 Testing



George Santagiuliana
 Approved Signature

12/02/2021

This certificate replaces previous certificate number 1111-20, issue 0 dated (REASON: Test Data Updated)