

CERTIFICATE OF ANALYSIS

**CERTIFICATE No.** 0351-19  
**TEST CERTIFICATE FOR:** Slag Blend 30  
**PRODUCED AT:** Sunstate Cement Ltd, Port of Brisbane  
**SAMPLE IDENTIFICATION:** Spot Despatch Sample sample O6P-000653 sampled on 18/3/2019  
**SAMPLE TESTED AT:** Sunstate Cement Ltd, Port of Brisbane


SPECIFIED PROPERTY	TEST METHOD	AS3972 REQUIREMENTS		RESULT
Compressive strength	AS2350.11, AS2350.12			
3 day				28.7 MPa
7 day		Minimum	20 MPa	40.8 MPa
28 day		Minimum	35 MPa	59.2 MPa
Setting time	AS2350.4			
Initial		Minimum	45 mins	105 mins
Final		Maximum	600 mins	165 mins
Soundness	AS2350.5	Maximum	5 mm	1 mm
Sulphuric anhydride (SO <sub>3</sub> )	In house	Maximum	3.5 %	3.0 %

REPORTABLE PROPERTY	TEST METHOD			RESULT
Loss on ignition	AS2350.2			2.9 %
Fineness	AS2350.8			435 m <sup>2</sup> /kg
Chloride	AS3583.13			0.0034 %

OTHER PROPERTIES	TEST METHOD			RESULT
Normal Consistency	In House			31.7 %

**SAMPLING PROCEDURE:** Cement samples obtained according to the requirements of AS2350.1

**REMARKS:** The results of the above tests relate only to the sample as described above.  
The blended cement is produced with a nominal 30% GBFS content.



**G Santaguiliana**  
**Approved Signatory**  
**19-Jun-2019**



NATA accredited laboratory  
Laboratory Number: 2190 / 2191  
Accredited for compliance with  
ISO/IEC 17025  
The results of the tests,  
calibrations and/or measurements  
included in this document are  
traceable to Australian/national  
standards. This document shall not  
be reproduced except in full.