

# Certificate Of Analysis

Certificate Number: **0025-21** Issue Number: **1** Issue Date: **26/03/2021 3:15:01 PM**  
 Test Certificate for: **SUNLITE Cement**  
 Sample Tested at: **Sunstate Cement Ltd., Port of Brisbane, Australia**  
 Sample Identification: **Spot Despatch Sample L6P-001342 dated 18/01/2021**  
 Sample Produced at: **Sunstate Cement Ltd., Port of Brisbane, Australia**

SPECIFIC PROPERTY	TEST METHOD	AS3972 REQUIREMENTS		RESULT
<b>Compressive strength</b>	AS2350.11, AS2350.12			
3 Day		Minimum	25 MPa	<b>39.6 MPa</b>
7 Day		Minimum	40 Mpa	<b>49 MPa</b>
28 Day				<b>61 MPa</b>
<b>Setting Time</b>	AS2350.4			
Initial		Minimum	45 mins	<b>90 mins</b>
Final		Maximum	360 mins	<b>165 mins</b>
<b>Soundness</b>	AS2350.5	Maximum	5 mm	<b>1 mm</b>
<b>Sulphuric anhydride (SO<sub>3</sub>)</b>	In House	Maximum	3.5 %	<b>3.0 %</b>
<b>Chloride</b>	AS3583.13	Maximum	0.1 %	<b>0.016 %</b>
REPORTABLE PROPERTY	TEST METHOD			RESULT
Loss on ignition	AS2350.2			<b>4.6 %</b>
Fineness	AS2350.8			<b>445 m<sup>2</sup>/kg</b>
OTHER PROPERTIES	TEST METHOD			RESULT
Normal Consistency	AS2350.3			<b>29.2 %</b>

**Sampling Procedure:**

Samples were prepared in accordance with AS2350.1

**Remarks:**

- 1 These results only relate to the specimens identified on this report



NATA accredited  
 Laboratory Number: 2191

Accredited for compliance with  
 ISO/IEC 17025 Testing



George Santagiuliana  
 Approved Signature  
 26/03/2021

***This certificate replaces previous certificate number 0025-21, issue 0 dated (REASON: Test Data Updated)***