

CERTIFICATE OF ANALYSIS

CERTIFICATE No. 0082-20
TEST CERTIFICATE FOR: Sunlite
PRODUCED AT: Sunstate Cement Ltd, Port of Brisbane
SAMPLE IDENTIFICATION: Spot Despatch Sample sample L6P-001293 sampled on 3/2/2020
SAMPLE TESTED AT: Sunstate Cement Ltd, Port of Brisbane

SPECIFIED PROPERTY	TEST METHOD	AS3972 REQUIREMENTS		RESULT
Compressive strength	AS2350.11, AS2350.12			
3 day		Minimum	25 MPa	42.6 MPa
7 day		Minimum	40 MPa	51.7 MPa
28 day				62.3 MPa
Setting time	AS2350.4			
Initial		Minimum	45 mins	75 mins
Final		Maximum	360 mins	120 mins
Soundness	AS2350.5	Maximum	5 mm	1 mm
Sulphuric anhydride (SO ₃)	In House	Maximum	3.5 %	3.2 %

REPORTABLE PROPERTY	TEST METHOD	RESULT
Loss on ignition	AS2350.2	4.7 %
Fineness	AS2350.8	450 m ² /kg
Chloride	AS3583.13	0.0131 %

OTHER PROPERTIES	TEST METHOD	RESULT
Normal Consistency	In House	28.7 %

SAMPLING PROCEDURE: Cement samples obtained according to the requirements of AS2350.1

REMARKS: The results of the above tests relate only to the sample as described above.



G Santaguiliana
Approved Signatory
28-Apr-2020

Page 1 of 1

A.B.N. 58 010 421 879
 POSTAL ADDRESS: PO BOX 350, WYNNUM, QLD. 4178
 PHONE: (07) 3895 9800 FAX: (07) 3895 9801



NATA accredited laboratory
 Laboratory Number: 2191
 Accredited for compliance with
 ISO/IEC 17025 Testing.
 The results of the tests,
 calibrations and/or measurements
 included in this document are
 traceable to Australian/national
 standards. This document shall
 not be reproduced except in full.